

## Product Data Sheet EP CC 301

910074

Property	Method of test	Unit	max. or min.	Ref. Value IEC 60893-3-2	Test value (median)
----------	----------------	------	--------------	--------------------------	---------------------

### Mechanische Eigenschaften

Flexural stress at rupture perpendicular to laminations	ISO 178	MPa	min.	<b>135</b>	160,73
Apparent modulus of elasticity in flexure	ISO 178	MPa	min.	6000*	7610
Compressive strength perpendicular to laminations	ISO 604	MPa	min.	230*	255,96
Impact strength (Charpy) parallel to laminations	ISO 179/3C	kJ/m <sup>2</sup>	min.	<b>6</b>	46,77
Shearing strength parallel to laminations	VDE 0318/2	MPa	min.	10*	46,47
Tensile strength	ISO 527-4	MPa	min.	100*	140,09

### Elektrische Eigenschaften

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.	<b>5**</b>	13,29
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	<b>35</b>	60
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	<b>1.000</b>	
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.	600*	600
Tracking and erosion resistance	IEC 60112	Klasse	min.		

### Sonstige Eigenschaften

Thermal endurance	IEC 60216	T.I.		130*	
Density	ISO 1183	g/cm <sup>3</sup>		1,2 - 1,4*	1,330
Water absorption, absolute	ISO 62	mg	max.	<b>100***</b>	

Base material: fine woven cotton cloth  
Matrix resin: Epoxy (epoxide)

\* Typical values as per IEC 60893-4. They shall not be considered as specification requirements.

\*\* for thickness  $\geq 3,0$  mm

\*\*\* for test specimens 50 x 50 x 4 mm

Test values are derived from an average type test

### RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive **2011/65/EU**, article 4, paragraph 1