

## Product Data Sheet EP GC 201 white

1720030

Property	Method of test	Unit	max. or min.	Ref. Value IEC 60893-3-2	Test value (median)
----------	----------------	------	--------------	--------------------------	---------------------

### Mechanical properties

Flexural stress at rupture perpendicular to laminations	ISO 178	MPa	min.	<b>340</b>	A 664,96 B 525,76
Apparent modulus of elasticity in flexure	ISO 178	MPa	min.	22000*	A 23819 B 21786
Compressive strength perpendicular to laminations	ISO 604	MPa	min.	350*	422,89
Impact strength (Charpy) parallel to laminations	ISO 179/3C	kJ/m <sup>2</sup>	min.	<b>42</b>	A 123,84 B 119,53
Shearing strength parallel to laminations	VDE 0318/2	MPa	min.	30*	
Tensile strength	ISO 527-4	MPa	min.	300*	A 398,16 B 322,96

### Electrical properties

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.	<b>10,2**</b>	13,47
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	<b>45</b>	50
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	<b>50.000</b>	189.750
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.	200*	220
Tracking and erosion resistance	IEC 60112	Klasse	min.		

### other properties

Thermal endurance	IEC 60216	T.I.		130*	
Density	ISO 1183	g/cm <sup>3</sup>		1,8 - 2,0*	1,902
Water absorption, absolute	ISO 62	mg	max.	<b>23***</b>	8,80

Base material: glass cloth  
Matrix resin: Epoxy (epoxide) white

\* Typical values as per IEC 60893-4. They shall not be considered as specification requirements.

\*\* for thickness  $\geq 3,0$  mm

\*\*\* for test specimens 50 x 50 x 4 mm

Test values are derived from an average type test

### RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive 2011/65/EU, article 4, paragraph 1