

Product Data Sheet EP PC 301

710152

Property	Method of test	Unit	max. or min.	Ref. Value IEC 60893-3-2	Test value (median)
----------	----------------	------	--------------	--------------------------	---------------------

Mechanical properties

Flexural stress at rupture perpendicular to laminations	ISO 178	MPa	min.	140	151,95
Apparent modulus of elasticity in flexure	ISO 178	MPa	min.	3000*	3904
Compressive strength perpendicular to laminations	ISO 604	MPa	min.	200*	
Impact strength (Charpy) parallel to laminations	ISO 179/3C	kJ/m ²	min.	55	194,63
Shearing strength parallel to laminations	VDE 0318/2	MPa	min.	12*	
Tensile strength	ISO 527-4	MPa	min.	135*	155,57

Electrical properties

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.	10,2**	12,66
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	45	70
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	1.000	2.000.000
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.	380*	360
Tracking and erosion resistance	IEC 60112	Klasse	min.		

other properties

Thermal endurance	IEC 60216	T.I.		130*	
Density	ISO 1183	g/cm ³		1,2 - 1,4*	1,320
Water absorption, absolute	ISO 62	mg	max.	160***	28,70

Base material: Polyester fibre cloth

Matrix resin: Epoxy (epoxide)

* Typical values as per IEC 60893-4. They shall not be considered as specification requirements.

** for thickness $\geq 3,0$ mm

*** for test specimens 50 x 50 x 4 mm

Test values are derived from an average type test

RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive 2011/65/EU, article 4, paragraph 1