

## Product Data Sheet PF CC 201 + PTFE

Property	Method of test	Unit	max. or min.	Nominal Value	Test value (median)
----------	----------------	------	--------------	---------------	---------------------

### Mechanical properties

Flexural stress at rupture perpendicular to laminations	ISO 178	MPa	min.	100	A 136,65 B 124,93
Apparent modulus of elasticity in flexure	ISO 178	MPa	min.	7000	A 7088 B 6341
Compressive strength perpendicular to laminations	ISO 604	MPa	min.	200	278,58
Impact strength (Charpy) parallel to laminations	ISO 179/3C	kJ/m <sup>2</sup>	min.	20	A 34,21 B 36,70
Shearing strength parallel to laminations	VDE 0318/2	MPa	min.	30	A 39,67 B 35,15
Tensile strength	ISO 527-4	MPa	min.	60	A 79,94 B 67,90

### Electrical properties

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.	0,5	0,95
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	1	3
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	1	6
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.	100	130
Tracking and erosion resistance	IEC 60112	Class	min.		

### other properties

Thermal endurance	IEC 60216	T.I.		120	120
Density	ISO 1183	g/cm <sup>3</sup>		1,3 - 1,4	1,375
Water absorption, absolute	ISO 62	%	max.	1,5	1,04
coefficient of friction $\mu$					0,107
linear rate of wear		mg/km			0,96

Base material Woven cotton cloth  
Matrix resin: Phenolic with PTFE additive

### RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive 2011/65/EU, article 4, paragraph 1