

Product Data Sheet PF CC 203 + PTFE

Property	Method of test	Unit	max. or min.	Nominal Value	Test value (median)
----------	----------------	------	--------------	---------------	---------------------

Mechanical properties

Flexural stress at rupture perpendicular to laminations	ISO 178	MPa	min.	110	A 140,69 B 146,82
Apparent modulus of elasticity in flexure	ISO 178	MPa	min.	7000	A 7555 B 7658
Compressive strength perpendicular to laminations	ISO 604	MPa	min.		285,07
Impact strength (Charpy) parallel to laminations	ISO 179/3C	kJ/m ²	min.	7	A 35,67 B 32,62
Shearing strength parallel to laminations	VDE 0318/2	MPa	min.	25	A 31,56 B 32,62
Tensile strength	ISO 527-4	MPa	min.	85	A 91,34 B 99,43

Electrical properties

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.	0,5	1,64
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	1	3
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	1	84
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.	100	120
Tracking and erosion resistance	IEC 60112	Class	min.		

other properties

Thermal endurance	IEC 60216	T.I.		120	
Density	ISO 1183	g/cm ³		1,3 - 1,4	1,407
Water absorption 50 x 50 x 10	ISO 62	mg	max.	319	231,80
coefficient of friction μ					0,107
linear rate of wear		mg/km			0,96

Base material Woven cotton cloth
Matrix resin: Phenolic with PTFE additive

RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive 2011/65/EU, article 4, paragraph 1