

Product Data Sheet PF GC 201

1350239

Property	Method of test	Unit	max. or min.	Ref. Value IEC 60893-3-4	Test value (median)
----------	----------------	------	--------------	--------------------------	---------------------

Mechanical properties

Flexural stress at rupture perpendicular to laminations	ISO 178	MPa	min.	140	A 345,21 B 331,16
Apparent modulus of elasticity in flexure	ISO 178	MPa	min.	14000*	A 23245 B 22481
Compressive strength perpendicular to laminations	ISO 604	MPa	min.		
Impact strength (Charpy) parallel to laminations	ISO 179/3C	kJ/m ²	min.	35	A 50,58 B 60,64
Shearing strength parallel to laminations	VDE 0318/2	MPa	min.		
Tensile strength	ISO 527-4	MPa	min.	100*	A 194,96 B 221,87

Electrical properties

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.	5,7**	6,97
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	20	40
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	100	13.010
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.	100*	120
Tracking and erosion resistance	IEC 60112	Klasse	min.		

other properties

Thermal endurance	IEC 60216	T.I.		120*	
Density	ISO 1183	g/cm ³		1,6 - 1,8*	1,778
Water absorption, absolute	ISO 62	mg	max.	178***	17,00

Base material: glass cloth
Matrix resin: Phenolic

* Typical values as per IEC 60893-4. They shall not be considered as specification requirements.

** for thickness $\geq 3,0$ mm

*** for test specimens 50 x 50 x 4 mm

Test values are derived from an average type test

RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive 2011/65/EU, article 4, paragraph 1