

## Product Data Sheet PF CC 41

Property	Method of testing	Unit	max. or min.	Ref. Value DIN EN 61212-3-3	Test value (median)
----------	-------------------	------	--------------	-----------------------------------	------------------------

### Mechanical properties

Flexural stress at rupture, perpendicular to laminations	ISO 178	MPa	min.	<b>125</b>	157,33
Compressive strength parallel to laminations (axial)	ISO 604	MPa	min.	<b>90</b>	124,57
Cohesion between layers	IEC 61212-2	MPa	min.		

### Electrical properties

Electric strength at 90°C in oil perpendicular to laminations	IEC 60243-1	kV/mm	min.		
Breakdown voltage at 90°C in oil parallel to laminations	IEC 60243-1	kV	min.	<b>5</b>	20
Insulation resistance after immersion in water	IEC 60167	MOhm	min.	<b>5</b>	6
Proof tracking index PTI	IEC 60112	PTI			
Comparative tracking index CTI	IEC 60112	CTI	min.		
Tracking resistance	IEC 60112	Klasse	min.		

### other properties

Thermal endurance	IEC 60216	T.I.		120*	
Density	ISO 1183	g/cm <sup>3</sup>		1,20 - 1,40*	1,354
Water absorption, absolute	ISO 62	mg/cm <sup>2</sup>	max.	<b>5</b>	2,65
coefficient of friction $\mu$					
linear rate of wear		mg/km			

Base material Fine woven cotton cloth  
Matrix resin: Phenolic

\* Are typical values intended to give only general guidance and are not to be considered as requirement of this standard.

### RoHS- Declaration

This material does not contain any substances of very high concern as listed in the EU directive 2011/65/EU, article 4, paragraph 1